



TAKIM ÇELİKLERİNİN TORNALAMA BİLGİLERİ

		HSS TAKIM RAPIDUR 3207			
		KABA İŞLEME		HASSAS İŞLEME	
Malzeme- DEW	Teslimat durumu	Kesme Hızı-Vc (m/dak.)	Besleme Hızı-fz (mm/devir)	Kesme Hızı- Vc (m/dak.)	Beslenme Hızı-fz (mm/devir)
Cryodur 1730	Tavlı	20 - 40	0.20 - 0.40	40 - 70	0.10 - 0.20
Formadur 2083	Tavlı	15 - 25	0.20 - 0.40	25 - 50	0.10 - 0.20
Formadur 2312	Ön-sertleştirilmiş	15 - 30	0.20 - 0.40	35 - 60	0.10 - 0.20
Thermodur 2343	Tavlı	15 - 25	0.20 - 0.40	25 - 50	0.10 - 0.20
Thermodur 2344	Tavlı	15 - 25	0.20 - 0.40	25 -50	0.10 - 0.20
Thermodur 2365	Tavlı	15 - 25	0.20 - 0.40	25 - 50	0.10 - 0.20
Thermodur 2367	Tavlı	15 - 25	0.20 - 0.40	25 - 50	0.10 - 0.20
Cryodur 2379	Tavlı	10 - 20	0.20 - 0.40	20 - 30	0.10 - 0.20
Thermodur 2714	Ön-sertleştirilmiş	10 - 20	0.20 - 0.40	20 - 30	0.10 - 0.20
Thermodur 2782	Çökelti tavllanmış	15 - 25	0.20 - 0.40	25 - 50	0.10 - 0.20
Thermodur 2787	Ön-sertleştirilmiş	10 - 20	0.20 - 0.40	20 - 30	0.10 - 0.20
Cryodur 2842	Tavlı	15 - 30	0.20 - 0.40	35 - 60	0.10 - 0.20
Thermodur 2999	Çökelti tavllanmış	10 - 20	0.20 - 0.40	20 - 30	0.10 - 0.20
Thermodur E 38 K	Tavlı	15 - 25	0.20 - 0.40	25 - 50	0.10 - 0.20



TAKIM ÇELİKLERİNİN TORNALAMA BİLGİLERİ

		KARBÜR KESME TAKIMLARI			
		P25 / P30 TİAIN		P10 / P15	
		KABA İŞLEME		HASSAS İŞLEME	
Malzeme- DEW	Teslimat durumu	Kesme Hızı-Vc (m/dak.)	Besleme Hızı-fz (mm/devir)	Kesme Hızı- Vc (m/dak.)	Beslenme Hızı-fz (mm/devir)
Cryodur 1730	Tavlı	150 - 230	0.40 - 1.00	300 - 420	0.10 - 0.40
Formadur 2083	Tavlı	125 - 195	0.40 - 1.00	250 - 370	0.10 - 0.40
Formadur 2312	Ön-sertleştirilmiş	130 - 200	0.40 - 1.00	270 - 390	0.10 - 0.40
Thermodur 2343	Tavlı	125 - 195	0.40 - 1.00	250 - 370	0.10 - 0.40
Thermodur 2344	Tavlı	125 - 195	0.40 - 1.00	250 - 370	0.10 - 0.40
Thermodur 2365	Tavlı	125 - 195	0.40 - 1.00	250 - 370	0.10 - 0.40
Thermodur 2367	Tavlı	125 - 195	0.40 - 1.00	250 - 370	0.10 - 0.40
Cryodur 2379	Tavlı	115 - 175	0.40 - 1.00	235 - 350	0.10 - 0.40
Thermodur 2714	Ön-sertleştirilmiş	115 - 175	0.40 - 1.00	235 - 350	0.10 - 0.40
Thermodur 2782	Çökelti tavllanmış	125 - 195	0.40 - 1.00	250 - 370	0.10 - 0.40
Thermodur 2787	Ön-sertleştirilmiş	115 - 175	0.40 - 1.00	235 - 350	0.10 - 0.40
Cryodur 2842	Tavlı	130 - 200	0.40 - 1.00	270 - 390	0.10 - 0.40
Thermodur 2999	Çökelti tavllanmış	115 - 175	0.40 - 1.00	235 - 350	0.10 - 0.40
Thermodur E 38 K	Tavlı	125 - 195	0.40 - 1.00	250 - 370	0.10 - 0.40