

**TAKIM ÇELİKLERİNİN DELME BİLGİLERİ**

<b>KESME HIZI (m/dak)</b>				
<b>Malzeme</b>	<b>Teslim Durumu</b>	<b>Rapidur 3343-3243</b>	<b>Rapidur 3343- 3243 + TİN</b>	<b>HM K 10</b>
Cryodur 1730	Tavlı	14.00 - 20.00	25.00 - 30.00	60 - 100
Formadur 2083	Tavlı	8.00 - 14.00	18.00 - 23.00	40 - 60
Formadur 2312	Ön sertleştirilmiş	10.00 - 16.00	20.00 - 25.00	50 - 80
Thermodur 2343	Tavlı	8.00 - 14.00	18.00 - 23.00	40 - 60
Thermodur 2344	Tavlı	8.00 - 14.00	18.00 - 23.00	40 - 60
Thermodur 2365	Tavlı	8.00 - 14.00	18.00 - 23.00	40 - 60
Thermodur 2367	Tavlı	8.00 - 14.00	18.00 - 23.00	40 - 60
Cryodur 2379	Tavlı	6.00 - 10.00	15.00 - 20.00	30 - 50
Thermodur 2714	Ön sertleştirilmiş	15.00 - 20.00	15.00 - 20.00	30 - 50
Cryodur 2842	Tavlı	20.00 - 25.00	20.00 - 25.00	50 - 80
Thermodur 2999	Tavlı	18.00 - 23.00	18.00 - 23.00	40 - 60
Thermodur E 38 K	Tavlı	18.00 - 23.00	18.00 - 23.00	40 - 60

**TAKIM ÇELİKLERİNİN DELME BİLGİLERİ**

<b>BESLEME HIZI (mm/devir)</b>				
<b>Malzeme</b>	<b>Teslim Durumu</b>	<b>Rapidur 3343-3243</b>	<b>Rapidur 3343- 3243 + TİN</b>	<b>HM K 10</b>
Cryodur 1730	Tavlı	0.04 - 0.20	0.16 - 0.25	0.06 - 0.30
Formadur 2083	Tavlı	0.04 - 0.14	0.12 - 0.20	0.06 - 0.20
Formadur 2312	Ön sertleştirilmiş	0.04 - 0.20	0.16 - 0.25	0.06 - 0.30
Thermodur 2343	Tavlı	0.04 - 0.14	0.12 - 0.20	0.06 - 0.20
Thermodur 2344	Tavlı	0.04 - 0.14	0.12 - 0.20	0.06 - 0.20
Thermodur 2365	Tavlı	0.04 - 0.14	0.12 - 0.20	0.06 - 0.20
Thermodur 2367	Tavlı	0.04 - 0.14	0.12 - 0.20	0.06 - 0.20
Cryodur 2379	Tavlı	0.04 - 0.16	0.12 - 0.20	0.06 - 0.20
Thermodur 2714	Ön sertleştirilmiş	0.04 - 0.16	0.12 - 0.20	0.06 - 0.20
Cryodur 2842	Tavlı	0.04 - 0.20	0.16 - 0.25	0.06 - 0.30
Thermodur 2999	Tavlı	0.04 - 0.14	0.12 - 0.20	0.06 - 0.20
Thermodur E 38 K	Tavlı	0.04 - 0.14	0.12 - 0.20	0.06 - 0.20

**TAKIM ÇELİKLERİNİN DELME BİLGİLERİ**

<b>MATKAP ÇAPI (mm)</b>				
<b>Malzeme</b>	<b>Teslim Durumu</b>	<b>Rapidur 3343-3243</b>	<b>Rapidur 3343- 3243 + TİN</b>	<b>HM K 10</b>
Cryodur 1730	Tavlı	8.00 - 16.00	8.16 - 16.00	20.00 - 47.00
Formadur 2083	Tavlı	8.00 - 16.00	8.16 - 16.00	20.00 - 47.00
Formadur 2312	Ön sertleştirilmiş	8.00 - 16.00	8.16 - 16.00	20.00 - 47.00
Thermodur 2343	Tavlı	8.00 - 16.00	8.16 - 16.00	20.00 - 47.00
Thermodur 2344	Tavlı	8.00 - 16.00	8.16 - 16.00	20.00 - 47.00
Thermodur 2365	Tavlı	8.00 - 16.00	8.16 - 16.00	20.00 - 47.00
Thermodur 2367	Tavlı	8.00 - 16.00	8.16 - 16.00	20.00 - 47.00
Cryodur 2379	Tavlı	8.00 - 16.00	8.16 - 16.00	20.00 - 47.00
Thermodur 2714	Ön sertleştirilmiş	8.00 - 16.00	8.16 - 16.00	20.00 - 47.00
Cryodur 2842	Tavlı	8.00 - 16.00	8.16 - 16.00	20.00 - 47.00
Thermodur 2999	Tavlı	8.00 - 16.00	8.16 - 16.00	20.00 - 47.00
Thermodur E 38 K	Tavlı	8.00 - 16.00	8.16 - 16.00	20.00 - 47.00